

ULTRA PREMIUM
SATIN ENAMEL

RESOURCE CODE 11530-Line

SEPTEMBER 2021

PAGE 1 OF 3



INTERIOR



EXTERIOR



CLEAN UP



Description & Uses

Wattyl Killrust Satin Enamel is a single pack, fast drying anti-corrosive topcoat designed with a satin sheen level and factory tinted to match popular Colorbond® colours. Killrust Satin Enamel is ideal for use on pre-coated metal surfaces where touching up and colour matching is required. It is available in an aerosol pack which means it is easy to use and equipment cleanup isn't required.

Features & Benefits

- Fast Drying
- Anti-Corrosive Formula
- Matches Popular Colorbond® Colours

Colours

Factory tinted to 20 standard Colorbond® colours.

Satin (Gloss level 30-35 at 60 degrees)

Properties & Performance Guide

Dry & Recoat Times	Surface Dry - 30 minutes Recoat - 24 hours Fully Cured - 7 days Figures are quoted at 25°C and at 50% humidity. Drying will take longer at lower temperatures or higher relative humidity.
Coverage per Coat	Up to 2 M ² /300g depending on the surface texture, porosity and film build applied.
Clean Up	Clean up with mineral turps away from drains. Soak all used cloths in water after use as they may self-ignite. Protect Our Environment: Do not pour leftover paint down the drain. Unwanted paint should be kept in a sealed container, and then disposed of via special waste collection services. Empty paint containers should be left open in a well ventilated area to dry out. Disposal of empty paint containers may differ between local authorities. Check with your local council first.

ULTRA PREMIUM
SATIN ENAMEL

RESOURCE CODE 11530-Line

SEPTEMBER 2021

PAGE 2 OF 3

Recommended Substrate Conditions & Preparation

Surfaces are to be suitably prepared in accordance with proper trade practices.

Killrust Satin Enamel is suitable for use on most metal surfaces.

Remove all traces of oil, grease and wax by wiping down the surface with mineral turps. Ensure all surfaces are clean and dry. Remove all loose rust scale, peeling and flaking paint by wire brushing or scraping. Sand smooth and remove dust.

Aluminium Surfaces:

New Unpainted – Apply one (1) coat of Killrust Etch Primer (D2.08). Topcoat after one (1) hour and within forty-eight (48) hours to avoid surface contamination.

Steel or Wrought Iron Surfaces:

New Unpainted – Apply one (1) coat of Killrust Heavy Duty Primer (D2.11).

Rusted – Treat with Killrust Rust-Eater (D1.10) and allow twenty-four (24) hours to dry. Apply one (1) coat of Killrust Heavy Duty Primer (D2.11), allowing four (4) hours to dry before topcoating.

Application Guide

Shake the aerosol for a full minute before use **after** hearing the mixing pellet rattle, and from time to time during use.

Apply only outdoors or in a well-ventilated area.

Protect nearby surfaces from overspray by covering or masking.

For best results spray at room temperature.

Hold the can upright approximately 25cm from the surface and maintain this distance during application. Spray with slow even strokes. Begin and end each stroke beyond the surface being painted.

If the spray jet becomes blocked, remove and clean the jet with fine wire and mineral turps. Do not insert sharp objects into the valve opening of the can.

After use, turn the can upside down and spray until the valve is clear of paint. Wipe the nozzle clean.

Do not apply when temperature is below 10°C or above 35° or when humidity is very high. The temperature must not fall below 10°C during the drying process.

In exterior application avoid painting when rain or dew is likely.

Additional Data

Available in 300g Aerosol.

Avoid exposure to steam and condensation for 48 hours after application of final coat.

Leave 7 days after application of final coat before washing. Wash using a sponge or soft cloth with warm water and mild detergent. Avoid harsh scrubbing and strong household cleaners.

Containers must be secured and stored upright during transit.

Containers must not be exposed to excessive heat or cold.

Store in a secure, cool and well ventilated place.

The use of proprietary additives other than those manufactured by Wattyl is not recommended.

Do not use for any other purpose other than as specified in our literature.

ULTRA PREMIUM
SATIN ENAMEL

RESOURCE CODE 11530-Line

SEPTEMBER 2021

PAGE 3 OF 3

Safety Data

First Aid Instructions	For advice, contact the Poisons Information Centre on 131 126 (Australia), 0800 764 766 (New Zealand), or a doctor. If swallowed, do not induce vomiting. Give a glass of water to drink. If in eyes, wash out immediately with water. If inhaled remove from contaminated area to fresh air. If skin contact occurs, remove contaminated clothing and flush contaminated skin with water.
Safety Directions	FLAMMABLE. HAZARDOUS: Contains liquid hydrocarbons. Keep away from sources of ignition. No smoking. Keep closed when not in use. Keep out of reach of children. Avoid contact with skin and eyes. Ensure adequate ventilation during use. Avoid prolonged breathing of vapour. Wash hands thoroughly after use.
Further Information	For the latest information refer to the Safety Data Sheet available on our websites. Australia: www.wattyl.com.au or contact Wattyl Assist on 132 101. New Zealand: www.wattyl.co.nz or contact Wattyl Assist on 0800 825 7727.

1. This information is provided with respect to the listed Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand products. Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand, hereon referred to as "Hempel (Wattyl)," recommends that:

(a) You review the Technical Data Sheets (TDS) and Safety Data Sheets (SDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Hempel (Wattyl); (c) the product be transported and handled in accordance with the SDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in the TDS was prepared using information gathered during product development. While Hempel (Wattyl) endeavour to update this information and maintain the accuracy of its contents, Hempel (Wattyl) cannot guarantee that the information is wholly comprehensive.

3. Hempel (Wattyl) recommend that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest office of Hempel (Wattyl).

4. To the full extent permitted by law, the liability of Hempel (Wattyl) for breach of a condition or warranty implied into the contract for sale between Hempel (Wattyl) and you by law is limited at the election of Hempel (Wattyl) to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.

All brands and product names are registered trademarks of Hempel (Wattyl) Australia Pty Ltd ABN 40 000 035 914 and Hempel (Wattyl) New Zealand Pty Ltd 942 904 073 3692.

WATTYL ASSIST: Ph: 132 101 (AUSTRALIA)

Ph: 0800 825 7727 (NEW ZEALAND)