

ULTRA PREMIUM  
RUST-EETER®

RESOURCE CODE 114313

JUNE 2022

PAGE 1 OF 3



## Description &amp; Uses

Wattyl Killrust Rust-Eeter® converts rust to a useful metallic surface.

## Features &amp; Benefits

- Stops corrosion
- Provides superior bonding for primers

## Properties &amp; Performance Guide

Dry & Recoat Times	Surface Dry - 10-30 minutes. For heavier rust allow extra drying time. Recoat - 24 hours Figures are quoted at 25°C and at 50% humidity. Drying will take longer at lower temperatures or higher relative humidity.
Coverage per Coat	Up to 10-12 M <sup>2</sup> /L depending on the surface texture, porosity and method of application.
Thinning	Not required.
Clean Up	Clean up with Lacquer Thinner away from drains. Soak all used cloths in water after use as they may self-ignite. <b>Protect Our Environment:</b> Do not pour leftover paint down the drain. Unwanted paint should be kept in a sealed container, and then disposed of via special waste collection services. Empty paint containers should be left open in a well ventilated area to dry out. Disposal of empty paint containers may differ between local authorities. Check with your local council first.
VOC (Volatile Organic Compounds)	VOC < 695g/L

## Recommended Substrate Conditions &amp; Preparation

Surfaces are to be suitably prepared in accordance with proper trade practices.  
 Suitable for converting rust on steel and other ferrous metal surfaces.  
 Not intended for use as a heavy duty coating primer.  
 Not recommended for use under lacquers or two pack finishes such as epoxies.  
 Not suitable directly under water-based products, use Killrust Heavy Duty Primer first.  
 Remove all loose scale, peeling or flaking paint by wire brush. Remove grease, oil, dust or dirt by washing with degreaser and/or detergent. Rinse thoroughly with fresh water. Allow to dry.

ULTRA PREMIUM  
RUST-EETER®

RESOURCE CODE 114313

JUNE 2022

PAGE 2 OF 3

## Application Guide

Shake contents well before and during use.  
Apply one (1) coat to rusted area by brush, dipping or spraying.

**Scale and deep pitted formation:** Brush away loose flakes or scale with a wire brush to ensure effective penetration.

**Painted surfaces:** Where large rusted areas are developing, strip the paint away until clean metal appears. Where small pinhole rust spots are developing, no preparation is necessary.

**Prime** with one (1) coat of Killrust Heavy Duty Primer (D2.11). Apply two (2) coats of Killrust Epoxy Gloss Enamel (D4.59).

Avoid painting when air temperature is below 10°C (or likely to go below before paint can dry thoroughly) or above 35°C or when humidity is very high.  
In exterior application avoid painting when rain or dew is likely.

## Additional Data

Available in a 200ml bottle.  
Containers must be secured and stored upright during transit.  
Containers must not be exposed to excessive heat or cold.  
Store in a secure, cool and well ventilated place. Keep container tightly closed.  
The use of proprietary additives other than those manufactured by Wattyl is not recommended.  
Do not use for any other purpose other than as specified in our literature.

## Safety Data

<b>First Aid Instructions</b>	For advice, contact the Poisons Information Centre on 131 126 (Australia), 0800 764 766 (New Zealand), or a doctor. If swallowed, do not induce vomiting. Give a glass of water to drink. If in eyes, wash out immediately with water. If inhaled remove from contaminated area to fresh air. If skin contact occurs, remove contaminated clothing and flush contaminated skin with water.
<b>Safety Directions</b>	FLAMMABLE. HAZARDOUS: Contains liquid hydrocarbons. Keep away from sources of ignition. No smoking. Keep closed when not in use. Keep out of reach of children. Avoid contact with skin and eyes. Ensure adequate ventilation during use. Avoid prolonged breathing of vapour. Wash hands thoroughly after use.
<b>Further Information</b>	For the latest information refer to the Safety Data Sheet available on our websites. Australia: <a href="http://www.wattyl.com.au">www.wattyl.com.au</a> or contact Wattyl Assist on 132 101. New Zealand: <a href="http://www.wattyl.co.nz">www.wattyl.co.nz</a> or contact Wattyl Assist on 0800 825 7727.

ULTRA PREMIUM  
RUST-EETER®

RESOURCE CODE 114313

JUNE 2022

PAGE 3 OF 3

1. This information is provided with respect to the listed Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand products. Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand, hereon referred to as "Hempel (Wattyl)," recommends that:

(a) You review the Technical Data Sheets (TDS) and Safety Data Sheets (SDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Hempel (Wattyl); (c) the product be transported and handled in accordance with the SDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in the TDS was prepared using information gathered during product development. While Hempel (Wattyl) endeavour to update this information and maintain the accuracy of its contents, Hempel (Wattyl) cannot guarantee that the information is wholly comprehensive.

3. Hempel (Wattyl) recommend that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest office of Hempel (Wattyl).

4. To the full extent permitted by law, the liability of Hempel (Wattyl) for breach of a condition or warranty implied into the contract for sale between Hempel (Wattyl) and you by law is limited at the election of Hempel (Wattyl) to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.

All brands and product names are registered trademarks of Hempel (Wattyl) Australia Pty Ltd ABN 40 000 035 914 and Hempel (Wattyl) New Zealand Pty Ltd 942 904 073 3692.

WATTYL ASSIST: Ph: 132 101 (AUSTRALIA)

Ph: 0800 825 7727 (NEW ZEALAND)