

PREMIUM
CLEAN AIR LOW SHEEN ACRYLIC

RESOURCE CODE 43851239

APRIL 2024

PAGE 1 OF 3



Description & Uses

Wattyl Ultra Clean Air Low Sheen Acrylic is a washable, hard-wearing water-based paint which delivers a premium quality finish on residential and commercial interior walls. Combines the environmental benefit of low VOC with superior application properties, good hiding power and minimal odour.

Features & Benefits

- Uniform finish
- High washability, resists stains
- Smooth, even finish
- Low odour
- Superior opacity for a uniform finish
- Easy, fast application

Colours

White – Can be tinted to white base colours.

Low Sheen (Gloss level 5 - 10 at 60 degrees).

Environmental Data & Certifications



VOC – less than 3g/litre untinted or when tinted with Ecotint. VOC (Volatile Organic Compounds) calculations are based on APAS definition and are in accordance with Green Building Council requirements. Green Building Council standard for the maximum VOC level in interior low sheen wall paint is 16g/litre.

Properties & Performance Guide

Dry & Recoat Times	Surface Dry	- 30 minutes
	Recoat	- 2 hours
Coverage per Coat	Fully Cured	- 7 days
	Figures are quoted at 25°C and at 50% humidity. Drying will take longer at lower temperatures or higher relative humidity.	
Film Thickness	Up to 16 M ² /L depending on the surface texture, porosity and method of application.	
	Wet Film Thickness (WFT)	- 62 microns minimum
	Dry Film Thickness (DFT)	- 23 microns minimum

PREMIUM
CLEAN AIR LOW SHEEN ACRYLIC

RESOURCE CODE 43851239

APRIL 2024

PAGE 2 OF 3

Thinning	Thinning is generally not required. If necessary to aid spray atomisation, thin with up to 5% water.
Clean Up	Clean up with cold water away from drains. Protect Our Environment: Do not pour leftover paint down the drain. To dispose of unwanted paint see paintback.com.au . Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle containers via recycling programs. Check with your local council first.
VOC (Volatile Organic Compounds)	VOC < 3g/Litre.

Recommended Substrate Conditions & Preparation

Surfaces are to be suitably prepared in accordance with proper trade practices. Ensure the surface is clean, dry and free from dust, dirt and grease. All loose, peeling or flaking material must be removed. Sand enamel painted or other very smooth surfaces to remove gloss. Fill holes and cracks with a suitable filler and sand lightly to an even finish.

All new cement surfaces need to be fully cured (typically 4–6 weeks) prior to painting. Ensure surfaces are free of bond breakers, formwork release agents and curing compounds.

If mould is present, clean surface with household bleach then rinse well with clean water.

Test soundness of previously painted surfaces by cutting a small X in the paint with a sharp blade. Stick a piece of tape firmly over the X and pull off. If the paint pulls away, the surface is unsound. Repeat at random in a number of areas. Unsound surfaces should be stripped for best results.

Application Guide

Stir well before and during use with a broad paddle reaching to the bottom of the can and using an upward lifting action.

Apply two full, even coats by brush, roller or spray.
Use a quality synthetic brush or synthetic roller.
Use a medium nap (12mm pile) synthetic roller on smooth and semi-smooth surfaces.
Use a longer nap (20mm pile) synthetic roller on rough surfaces, e.g. Besser Block.
Use a 13 or 15 thou Tip for airless spray.
Do not apply when temperature is below 10°C or above 35°C or when humidity is very high.

Surface Type	Preparatory Coats
Previously painted surfaces, new paper-faced plasterboard, unpainted brick, cement render, fibre cement or masonry.	Apply one coat of Wattyl Ultra Prep Acrylic Sealer Undercoat.
Surface Type...Continued	Preparatory Coats...Continued
Bare timber and MDF.	Apply one coat of Wattyl Ultra Prep Acrylic Sealer Undercoat. On tannin rich timber first apply one coat of Wattyl Ultra Prep Primer Sealer Undercoat.
Bare plaster.	Apply one coat of Wattyl Master Prep Pigmented Sealer or Wattyl Acrylic Plaster Sealer.

Additional Data

PREMIUM
CLEAN AIR LOW SHEEN ACRYLIC

RESOURCE CODE 43851239

APRIL 2024

PAGE 3 OF 3

Available in 10 & 15 litre containers.

Tinted paint is non-refundable, so choose your colours carefully.

If this paint has been tinted, check that the colour is suitable for your requirements before application. For best results and colour consistency, tinted paint should be boxed and thoroughly mixed on site.

Avoid exposure to steam and condensation for 48 hours after application of final coat.

Leave 7 days after application of final coat before washing. Wash using a sponge or soft cloth with warm water and mild detergent. Avoid harsh scrubbing and strong household cleaners.

Containers must be secured and stored upright during transit.

Containers must not be exposed to excessive heat or cold.

Store in a secure, cool and well ventilated place. Keep container tightly closed.

The use of proprietary additives other than those manufactured by Wattyl is not recommended.

Do not use for any other purpose other than as specified in our literature.

Safety Data**First Aid Instructions**

For advice, contact the Poisons Information Centre on 131 126 (Australia), 0800 764 766 (New Zealand), or a doctor.
If swallowed, do not induce vomiting. Give a glass of water to drink.
If in eyes, wash out immediately with water.
If inhaled remove from contaminated area to fresh air.
If skin contact occurs, remove contaminated clothing and flush contaminated skin with water.

Safety Directions

Keep out of reach of children.
Avoid contact with skin and eyes.
Ensure adequate ventilation during use.
Avoid prolonged breathing of vapour.
Wash hands thoroughly after use.

Further Information

For the latest information refer to the Safety Data Sheet available on our websites.
Australia: www.wattyl.com.au or contact Wattyl Assist on 132 101.
New Zealand: www.wattyl.co.nz or contact Wattyl Assist on 0800 825 7727.

1. This information is provided with respect to the listed Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand products. Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand, hereon referred to as "Hempel (Wattyl)," recommends that:

(a) You review the Technical Data Sheets (TDS) and Safety Data Sheets (SDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Hempel (Wattyl); (c) the product be transported and handled in accordance with the SDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in the TDS was prepared using information gathered during product development. While Hempel (Wattyl) endeavour to update this information and maintain the accuracy of its contents, Hempel (Wattyl) cannot guarantee that the information is wholly comprehensive.

3. Hempel (Wattyl) recommend that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest office of Hempel (Wattyl).

4. To the full extent permitted by law, the liability of Hempel (Wattyl) for breach of a condition or warranty implied into the contract for sale between Hempel (Wattyl) and you by law is limited at the election of Hempel (Wattyl) to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.

All brands and product names are registered trademarks of Hempel (Wattyl) Australia Pty Ltd ABN 40 000 035 914 and Hempel (Wattyl) New Zealand Pty Ltd 942 904 073 3692.

INFORMATION HOTLINE: Ph: 132 101 (AUSTRALIA)

Ph: 0800 825 7727 (NEW ZEALAND)